

**IMPRESSION****HWU - 200A**Water Dispersed Polyurethane  
For Coating & Adhesive

DESCRIPTION	IMPRESSION HWU-200A is water dispersed polyurethane resin for coating and adhesive.
SPECIAL PROPERTIES	Contains no organic solvents or emulsifiers - Low VOC, - Less Hazard, - Less Toxicity, - Acceptable Environment High Lightfastness Formation of flexible film Good Resistance of Hydrolysis
CHEMICAL COMPOSITION	Anionic Polyether Polyurethane Dispersion Solid Content : 30% - Solvent : Water 67%, Cosolvent 3%
PROPERTIES of DISPERSION	Appearance : Semi Transparency pH : 7.2-7.5 Viscosity : 150 ±50 cPS/25 Density(25 ) : 1.02(g/cm <sup>3</sup> )
PROPERTIES of CASTING FILM	Appearance : Transparent 100% Modulus : 23 ±5 Kg/cm <sup>2</sup> Tensile Strength : 180 ±100 Kg/cm <sup>2</sup> Elongation : 400 ±100 %
HANDLING and STORAGE	IMPRESSION HWU - 200A can be stored for 6 months. Avoid exposure to temperatures above 50 for long periods. The product is sensitive to frost and must not be stored at temperatures below 5 . It cannot be thawed once it has frozen. Containers must be kept tightly sealed because otherwise a film which cannot be redispersed may form as result of evaporation of water. Packing : 125Kg Plastic Drum
NOTICE	The above enclosed system are designed to help you select system for typical system. For more information on IMPRESSION HWU-200A, simply return the product information request sheet via FAX and E-mail. The technical support formulation and application specialists at HEPCE CHEM are standing by to assist you... whatever your needs.

HEPCE CHEM Co., Ltd.

<http://www.hepce.com>E-mail : [hepce@hepce.com](mailto:hepce@hepce.com)

H/O &amp; Factory : TEL : +82-31-491-1611, FAX : +82-31-491-7400,

ShiWha Ind. 6BA-505, #683-4, Sunggok-dong, Ansan-City, Kyungki-Do, Korea, 425-110

R &amp; D Center : TEL : +82-31-417-0662, FAX : +82-31-417-0111

RM No. 412, Ansan Technopark, #1271, Sa -dong, Ansan-City, Kyungki-Do, Korea, 425-791